HAKOFT-700

Tip Polisher



- · Soldering tip polisher best suited to the removal of oxidation on soldering tips
- · Prevents the shortening of the service life of tips caused by oxidation.

Usage

Oxidized tip










Polished and retinned tip

Cleaning procedure



oxidation.

2. Quickly retin the

chemical paste

tip end.

4. Feed the solder wire to the tip.

* Approximately 300°C is the most suitable temperature for cleaning the tips.



Use the brush to remove tough oxide

Packing List

FT-700	Unit. Paste. Brush. Instruction manual

Specifications

Model No.	FT-700
Power consumption	3 W (100 V), 4.5 W (110 to 120 V, 220 to 240 V)
Dimensions	70 (W) × 54 (H) × 101 (D) mm
Weight*	0.65 kg

^{*} Without cord

·Chemical paste

Amount	10 g
Ingredients	Flux, tin (Sn) 50 wt% (each)

^{*} The flux component of chemical paste consists of alicyclic amine hydrobromate, aliphatic amine hydrobromate, petrolatum, and wax.

PIAK(O CHEMICAL PASTE

Chemical Paste





- · Chemical paste best suited to the removal of oxidation on soldering iron tips
- · Also used for retinning of soldering tips

Packing List

FS-100 Paste, Instruction manual

Specifications

·Chemical naste

onemous public	
Amount	10 g
Ingredients	Flux, tin (Sn) 50 wt% (each)

^{*} The flux component of chemical paste consists of alicyclic amine hydrobromate, aliphatic amine hydrobromate, petrolatum, and wax.